

PRODUCT DATA SHEET

CG POLYMERIC PERFORATED WINDOW FILM 70/30

Calendered polymeric gloss film with a 70/30 perforation. PPF70/30 is a dual layered film with a gloss white printable side and a black pressure sensitive adhesive side. Offered with a double PE release liner, compatible with Solvent, Eco Solvent, Uv and Latex printing technologies.

APPLICATIONS

- Shop Front and Building Windows
- Internal and External Windows and Glass Partitions

TECHNICAL DATA

Hole Diameter	Open rate	Film with glue thickness	liner	Width	Length	INK
1.5mm	70/30	170micron	210 double PE paper liner	1.37/1.52m	50,100 m	Solvent, ECO, UV.latex

Film	Composition	Glossy White/black Polymeric vinyl
	Thickness	150±5um GB/T6672-2001
	Shrinkage after application	Max 0.5mm (48 hours at 70degree, Aluminium, MD)
	Opacity	>99%
Hole	Hole size	1.5mm
	Hole distance	2.5mm
Adhesive	Adhesive Type	Clear Acrylic Solvent, pressure sensitive
	Thickness	20±2 um
	Initial Adhesion(20min)	10±2N/inch
	180 degree Peel (24hr)	13±2N/inch
	Holding Power	>800min
	Removable Durability	Permanent
Liner	Type	Double PE composite paper liner
	Weight	210g±10g/m2
	Release force	40g
	SA rate	>80%
Salt water testing		100h/23°C no variation

INSTALLATION

Before applying an overlamine, we suggest you allow 24-48 hours for the print to dry. Always clean application free of dust, dirt, debris and other contaminants. We recommend cleaning the installation surface with isopropyl alcohol prior to application.

All information stated within this Product Data Sheet is intended for reference purposes only. The information does not suggest or constitute a verbal or written warranty. The end user shall be responsible for the testing and suitability of their application prior to final use.